

POLYESTER RESIN

USE RECOMMENDATIONS

Used with the Fiberglass Blanket to perform repairs on fiber substrates in general

Chemical composition Unsaturated polyester resin

APPLICATION DATA

Catalysis and/or Dilution 100 parts by weight of Polyester Resin
25 drops of catalyst for Plastic Glue when the temperature is higher than 25°C, and 50 drops for temperatures lower than 25°C.

Application After catalysis, a coat is applied with a brush or roller (wool); then a layer of blanket and another layer of resin are placed. If you wish to apply more layers, wait for initial drying and repeat the procedure according to the number of layers you want.

Spreading Rate Each KG of resin covers 1m² of fiber blanket

DRYING

Drying time to touch is 5 to 10 minutes. Drying time for handling is 30 minutes. Final drying takes 2 hours.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

SURFACE PREPARATION

Remove excess paint residue until the existing fiber appears.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.