

NITROCELLULOSE LACQUER

USE RECOMMENDATIONS

Nitrocellulose-based finishing paint, quick-drying in air. Good flexibility and easy application. Indicated for general or partial painting of automotive vehicles and metal parts in general, previously prepared.

Chemical Composition

Alkyd resins, nitrocellulose, additives, aromatic hydrocarbons and oxygenated solvents, organic and inorganic pigments.

APPLICATION DATA

Catalysis and/or Dilution

100 parts by volume of Nitrocellulose Lacquer.
80 – 100 parts by volume of the Thinner 2900 or Eco-efficient 2900.

Application

Apply three to four crossed coats with compressed air pressure between 40 and 50 lb/in² and an interval of 5 to 10 minutes between coats.

Spreading Rate

8 -10m²/liter per 35µm dry layer

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

DRYING

Drying time to touch is 15 minutes. Drying time for handling is 30 minutes. Final drying takes 12 hours. In an oven at 60°C, drying takes 30 minutes.

SURFACE PREPARATION

Sand the surface eliminating rust or loose parts. Eliminate oily contaminants or dust with a cloth dampened with Anjo Degreaser solution. If necessary, correct defects in the leveling of glues with Anjo Plus Fast Filler, apply in crossed and thin layers. Sand after complete drying. In case of areas where the plate is exposed, apply Wash Primer. Afterwards, apply Anjo Universal Primer.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.