



## TECHNICAL NOTICE

FR413 (REV. 01)

### SPECIAL SERIES PLASTIC BODY FILLER

#### USE RECOMMENDATIONS

Suitable for leveling or correcting imperfections in automotive metal surfaces, machinery and equipment, marble and granite. We have the Special Series Plastic Body Filler in two colors: White and Grey.

#### Chemical Composition

Polyester resin, mineral fillers, additives, pigments and solvents.

#### APPLICATION DATA

#### Catalysis and/or Dilution

100 parts by weight of Special Series Plastic Body Filler.  
20 to 30 drops of catalyst for Special Series Plastic Body Filler.

#### Application

Mix the body filler well with the catalyst, and apply with an applicator. Do not reinsert the already prepared mixture into the can.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

Revision date: 12/29/2022

## **DRYING**

Drying time for sanding is between 1 and 2 hours. Sand with 60, 80 and 150 grit sandpaper.

## **SURFACE PREPARATION**

Sand the surface with 24 or 36-grit sandpaper to remove rust and traces of peeled paint. Anjo Paint Stripping Paste may also be used. Clean with Anjo Degreaser solution to eliminate dirt, oils, grease and residues in general. In case of parts with exposed chassis, the use of the Anjo Wash Primer is advised.

## **SAFETY RECOMMENDATION**

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

## **COMMENTS**

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.