

VINYL MATTE BLACK

USE RECOMMENDATIONS

With the same properties as an adhesion agent and a phosphatizing primer, Vinyl Matte Black is intended as a finishing paint for application on galvanized, aluminum, zinc, ferrous and non-ferrous metals.

Chemical Composition

Polyvinylbutyral resin, organic and inorganic pigments, aromatic hydrocarbons and alcohols.

APPLICATION DATA

Catalysis and/or Dilution

2 parts by volume Vinyl Matte Black
1 part by volume of Catalyst Wash Primer/ Vinyl Matte Black

Application

Apply 1 to 2 coats with a spray gun with 40 to 50 lb/in² air pressure. Vinyl Matte Black must not be diluted to avoid loss of its original characteristics of resistance and adherence.

Spreading Rate

10m²/liter/coat

DRYING

Drying time to touch is 10 minutes. Final drying takes 12 hours.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

SURFACE PREPARATION

Sand the surface eliminating rust or loose parts. Eliminate oily contaminants or dust with a cloth dampened with Anjo Degreaser solution.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.