



# TECHNICAL NOTICE

FR413 (REV. 01)

## HOOD SEALANT

### USE RECOMMENDATIONS

Product used for sealing finishes on car and truck bodies. Indicated for internal reinforcement of hoods, sills, floors, fenders, headlight compartments and places where a certain flexibility is required. Can be applied on top of bare metal, on top of primers and old paints.

#### Chemical Composition

Polyol of fatty acids, additives and mineral fillers.

### APPLICATION DATA

#### Catalysis and/or Dilution

100 parts by weight of Hood Sealant  
15 parts by weight of Catalyst for Hood Sealant

#### Application

Homogenize the Hood Sealant and the Catalyst until a uniform mass is formed. Apply on the desired surface using a spatula or brush. The product should be used within a maximum of 60 minutes after mixing.

#### Spreading Rate

May vary depending on the type of application

### DRYING

Final drying takes 24 hours.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

Revision date: 12/29/2022

## **SURFACE PREPARATION**

The surface on which the product will be applied should be cleaned well with a degreaser solution. Put an adhesive tape around the application site for a better finish.

## **SAFETY RECOMMENDATION**

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

## **COMMENTS**

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.