

GREEN ZINC CHROMATE SYNTHETIC PRIMER

USE RECOMMENDATIONS

One-component anti-corrosive primer with excellent spreading and fast drying properties. Anticorrosive protection occurs by the barrier and inhibition of anticorrosive pigment. Indicated as a primer and anticorrosive primer on metallic surfaces in general, such as tipper buckets, chassis, agricultural implements, machinery, industrial equipment, among others. When applied on aluminum, zinc and galvanized substrates, it is necessary to use Anjo Wash Primer or Anjo Primer for Galvanized Surfaces before application.

Chemical composition Alkyd resins, solvents, additives and pigments.

APPLICATION DATA

Catalysis and/or Dilution 15 to 20% by volume with the Thinner 2750 or Eco-efficient 2750.

Application Apply 1 to 2 crossed coats, or as needed with pressure of 40 to 60 lb/in² and an interval of 10 to 15 minutes between coats.

Spreading Rate 10m²/liter/coat

DRYING

Drying time to touch: 10 to 30 minutes

Drying for handling: 3 to 12 hours

Final drying: 72 hours

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

SURFACE PREPARATION

Sand the surface eliminating rust or loose parts. Eliminate oily contaminants or dust with a cloth dampened with Anjo Degreaser solution.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.