

SEALER FOR PLASTIC

USE RECOMMENDATIONS

Indicated to promote the adhesion of primers and paints on plastic parts, such as bumpers, mirrors, grooves, door handles, among others.

Chemical Composition Acrylic resins, aromatic hydrocarbons and additives.

APPLICATION DATA

Catalysis and/or Dilution Ready to use.

Application Apply one semi-wet coat or two powdered coats using a spray gun with pressure between 40 to 60lb/in², with an interval of 3 to 5 minutes between coats.

Spreading rate 7 m²/liter/coat

DRYING

After applying the sealant, wait approximately 10 minutes or until the part is matte and "sticky". Then, apply the desired product. It is important that this application be carried out within 10 minutes to avoid product displacement.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

SURFACE PREPARATION

Clean thoroughly with soap or neutral detergent and plenty of water. Use the degreaser solution so that the surface is completely free of any type of grease or other products that have been used. On parts that have a smooth surface, a matting process must be carried out with fine sandpaper.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.