

Anjo High Temperature Spray Paint

Made with high quality products, indicated and approved for use on external metallic surfaces at high temperatures up to 600°C, motorcycle and car exhaust pipes, fireplaces. If applied while observing the instructions, the Spray Paint ensures good coverage, with high spreading rate and excellent drying.

BASIC PROPERTIES

Technical Data:**Colors:** 3 line colors**Physical State:** Liquid / Pressed**Odor:** Characteristic**Explosive Limits:** Do not store above 50°C**pH:** Not applicable**Flash Point:** -70°C (Closed vessel)**Solubility:** Insoluble in water**Viscosity:** 20" to 30" CF3**Density:** 0.90 a 0.94 g/cm³**Internal Pressure:** 40 to 60 Psi at 50°C**Flow Rate:** 60 to 100 g/minute

Approximate Spreading rate: 1.0m² to 1.4m² per coat, recommended application 2 to 3 coats.

Drying: to the touch 20 minutes, handling 1 hour, and final 24 hours.

Packaging: 400 ml tube.

INSTRUCTIONS FOR USE

Surface preparation: The surface to be painted must be thoroughly cleaned and sanded (if necessary and if the surface supports it). It must be dry and free of grease, rust, remains of old paint, dust, resin, among others. To remove old paint, use Paint Stripper Putty or sandpaper. Protect the part that will not be painted.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

Application: Apply a maximum of 2 coats (interval of 5 to 15 minutes between coats). Make a small test of the applicator pressing the valve a few times checking the shape of the jet. Spray from a distance of 20 cm to 30 cm with even movements. Prevent run-off by applying the first coat thinly, preparing the surface for the next coat. Apply until coverage is complete. Do not apply any type of Primer to the surface. AFTER APPLICATION, WAIT FOR DRYING AND SUBMIT THE SUBSTRATE TO 250°C FOR 1 HOUR FOR CURING. With this procedure, the surface will have a resistance of up to 600°C.

Recommendations: Carry out a test on a small area to check the compatibility and drying of the product with the surface. We do not recommend using on wood and leather. Do not apply in very humid weather or at temperatures below 18°C, in which case it is recommended to leave the pieces in the sun before painting. Do not carry out the application in closed places or without air circulation. After use, clean the valve by turning the can upside down and pressing until only gas comes out. In case of valve clogging, remove the actuator and immerse it in acetone or any other solvent. When necessary, clean the hole with a very fine needle.

Storage: Keep in a covered and ventilated place (temperature below 50°C). Under these conditions, the product in its original, sealed packaging is guaranteed for 2 years from the date of manufacture.

Precautions: DANGER. Extremely flammable aerosol. Pressurized container: may rupture if heated. Causes skin irritation. Causes eye irritation. May cause drowsiness or dizziness. Toxic to aquatic organisms. Harmful to aquatic life with long lasting effects. Keep away from heat, sparks, open flames or hot surfaces. - Do not smoke near the product. Keep out of sunlight. Do not expose to temperatures above 50°C. IN CASE OF SKIN CONTACT: Wash with plenty of soap and water. IN CASE OF CONTACT WITH EYES: Rinse thoroughly with water for several minutes. If you wear contact lenses, remove them if possible. Keep rinsing. **Should not be used on the skin/body.**

Safety: Before using this or any other chemical product, make sure you have read and understood the information contained in the Material Safety Data Sheet (MSDS). Note the potential hazards and follow all precautionary measures, handling instructions, considerations and provisions mentioned on the SDS and on the packaging.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.