

EASY REPAIR

USE RECOMMENDATIONS

Product indicated for the correction of small imperfections on surfaces intended for repainting. Can be applied to correct small defects on polyester filler, primers and paints.

Chemical Composition

Alkyd resins, mineral fillers, additives, pigments, nitrocellulose-based solutions and solvents.

APPLICATION DATA

Catalysis and/or Dilution

Ready-to-use product.

Application

Apply with the celluloid or spatula on the defect, in thin and successive layers until obtaining the desired filling, with an interval of 3 to 10 minutes between coats.

DRYING

After application, allow to dry for 20 to 30 minutes and dry sand with 320 or 400 grit sandpaper.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

SURFACE PREPARATION

Sand the area to be repainted. Clean with Anjo Degreaser solution to eliminate dirt, oils, grease and residues in general.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.