

BUMPER REPAIR

USE RECOMMENDATIONS

Indicated for repairing bumpers, fenders and plastic parts in general (polyurethane and ABS) and fiberglass parts.

Chemical Composition

Component A: Epoxy resins and solvents.

Component B: Polyaminoamide resin and solvents

APPLICATION DATA

Catalysis and/or Dilution

1 part of Bumper Repair Component A

1 part of Bumper Repair Component B

Application

Paste a tape on the outside of the part to be repaired in order to protect it so that the mixture does not exceed.

Cut the fiber into pieces of different sizes, according to the size of the repair.

Mix the two components. Apply the first layer of the mixture and then place the smaller blanket. After that, alternate the application of the mixture and blanket, obeying the increasing order of the size of the blanket.

Press the plastic film in order to remove air bubbles and improve the adhesion of the blanket with the mixture.

After drying, carry out sanding.

Applying polyester filler over the Bumper Repair is not recommended.

Application on PVC is not recommended.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

DRYING

Drying for handling (25°C): 2 hours

Final drying (25°C): 24 hours

SURFACE PREPARATION

Sand the area to be repaired in order to improve the adhesion of the product to the substrate. Clean with Anjo Degreaser solution to eliminate dirt, oils, grease and residues in general.

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.