



TECHNICAL DATA SHEET

FR413 (REV. 01)

ADITIVO SLIP EON USO 5%

Auxiliary product indicated for use in flexographic and rotogravure printing inks. Composite of sliding solution and wax solution used to promote resistance to abrasion and baixo COF. It is recommended a dosage of 5% on the total volume of the ink. It can be used for the conversion of ink for external printing adding um bom brilho.

CODE: 038131-30

TYPICAL PROPERTIES

Product type..... Mixture
Aspect..... White cloudy liquid
Density..... 1,0 g/cm³ (20 °C) (approximate value)
Viscosity..... ≈ 300 cP (approximate value)
Non volatile..... ≥ 32,5%

DATA FOR APPLICATION

Dosage 5% in relation to the ink volume

APPLICATION INSTRUCTIONS

Shake the contents with a mechanical stirrer. Make sure no pigment is trapped at the bottom of the container. Adjust the viscosity only after its perfect homogenization. During printing, the reservoir, the inkwell and the tin should remain closed. In stock keep cans tightly closed in a cool and well-ventilated place.



TECHNICAL DATA SHEET

FR413 (REV. 01)

SAFETY RECOMMENDATION

Store the product in sheltered, ventilated environments.

Flammable product, keep away from sparks, sources of ignition, do not smoke.

Product when applied emanates vapors that should be avoided with the correct use of PPE, such as masks and respirators.

Avoid skin contact using gloves, goggles, proper clothing, protective creams etc.

Keep away from contact with children and animals.

STATUTORY REQUIREMENTS

ANVISA (Brazilian Health Regulatory Agency): Rules heavy metal levels for food packaging that may have contact with children;

FDA (Food and Drug Administration): Norm american regulating foods and drugs for toxicity;

ABRE (Associação Brasileira de Embalagens): Exclusion list to toxicity to inkd and solvente the print;

EUPIA (European Printing Ink Association): European exclusion list per toxicity in inks and solvent for printing.

OBSERVATION

The instructions in this bulletin are based on our experience and technical knowledge, however, some factors are independent of our control as a manufacturer, such as:

substrate treatment, application, working conditions, and so forth. Due to substrate diversity and printing conditions, this sheet is sent for proposed information and is offered without warranty as it must be confirmed by industrial testing before products are used.

Use of thinner other than specified may affect product performance.

ANJO TINTAS

UNIDADE IV – IMPRESSÃO

Rod. SC 108, s/n - Km 336 - B. São Simão - Morro da Fumaça - SC - CEP: 88830-000

Fones: (48)3461-8000 Fax: (48) 3461-8001

www.anjo.com.br



TECHNICAL DATA SHEET

FR413 (REV. 01)

Anjo is constantly making improvements to its products and we reserve the right to change the contents of this technical bulletin without prior notice. Anjo is not responsible for improper use of the product.

Shelf life 6 months

Packing

Metal bucket.....16Kg

Drum.....160Kg

Review 28/07/2020

ANJO TINTAS

UNIDADE IV – IMPRESSÃO

Rod. SC 108, s/n - Km 336 - B. São Simão - Morro da Fumaça - SC - CEP: 88830-000

Fones: (48)3461-8000 Fax: (48) 3461-8001

www.anjo.com.br