



TECHNICAL DATA SHEET

FR413 (REV. 01)

ADITIVO SLIP USO 4 A 6%

Auxiliary product indicated for use in flexo and gravure printing inks. Composite of sliding solution and wax solution used to promote abrasion resistance and low COF. Dosage of 4 to 6% of the total ink volume is recommended. Can be used for converting lamination inks for external printing.

CODE: 019483-00

TYPICAL PROPERTIES

Product type..... Mistura
Aspect..... White cloudy liquid
Density..... 1,0 g/cm³ (20 °C) (approximate value)
Viscosity..... ≈ 100 cP (approximate value)
Non volatile..... ≥ 32,5%

APPLICATION

Dosage 4 - 6% relative to the ink volume

APPLICATION INSTRUCTIONS

Shake the contents with a mechanical stirrer. Make sure no pigment is trapped at the bottom of the container. Adjust the viscosity only after its perfect homogenization. During printing, the reservoir, the inkwell and the tin should remain closed. In stock keep cans tightly closed in a cool and well-ventilated place.

ANJO TINTAS

Unit IV – ANJOPRINT

Rod. SC 108, s/n - km 366 - B. São Simão - Morro da Fumaça – SC/Brasil - CEP: 88830-000

Tel: +55.48.3461-8000 Fax: +55.48.3461-8001

www.anjo.com.br



TECHNICAL DATA SHEET

FR413 (REV. 01)

SAFETY RECOMMENDATION

Store the product in sheltered, ventilated environments.

Flammable product, keep away from sparks, sources of ignition, do not smoke.

Product when applied emanates vapors that should be avoided with the correct use of PPE, such as masks and respirators.

Avoid skin contact using gloves, goggles, proper clothing, protective creams etc.

Keep away from contact with children and animals.

STATUTORY REQUIREMENTS

ANVISA (Brazilian Health Regulatory Agency): Rules heavy metal levels for food packaging that may have contact with children;

FDA (Food and Drug Administration): Norm american regulating foods and drugs for toxicity;

ABRE (Associação Brasileira de Embalagens): Exclusion list to toxicity to inkd and solvente the print;

EUPIA (European Printing Ink Association): European exclusion list per toxicity in inks and solvent for printing.

OBSERVATION

The instructions in this bulletin are based on our experience and technical knowledge, however, some factors are independent of our control as a manufacturer, such as:

substrate treatment, application, working conditions, and so forth. Due to substrate diversity and printing conditions, this sheet is sent for proposed information and is offered without warranty as it must be confirmed by industrial testing before products are used.

Use of thinner other than specified may affect product performance.

ANJO TINTAS

Unit IV – ANJOPRINT

Rod. SC 108, s/n - km 366 - B. São Simão - Morro da Fumaça – SC/Brasil - CEP: 88830-000

Tel: +55.48.3461-8000 Fax: +55.48.3461-8001

www.anjo.com.br



TECHNICAL DATA SHEET

FR413 (REV. 01)

Anjo is constantly making improvements to its products and we reserve the right to change the contents of this technical bulletin without prior notice. Anjo is not responsible for improper use of the product.

Shelf life 6 months

Packing

Metal bucket.....13Kg

Drum.....150Kg

Review 28/07/2020

ANJO TINTAS

Unit IV – ANJOPRINT

Rod. SC 108, s/n - km 366 - B. São Simão - Morro da Fumaça – SC/Brasil - CEP: 88830-000

Tel: +55.48.3461-8000 Fax: +55.48.3461-8001

www.anjo.com.br