

## TECHCRIL 3152

One-component, solvent-based acrylic paint, easy to apply by roller, spray gun and airless spray. Developed for painting floors and demarcation strips. It has good flexibility, excellent abrasion resistance and quick drying, allowing the area to be released in a short time. It has good filling power and coverage, in addition to offering excellent resistance to the sun's ultraviolet rays.

### RECOMMENDED USES

Indicated for the demarcation of concrete or asphalt floors, on highways, parking yards or industrial floors (areas of production, storage, logistics, shipping, etc.), for signaling the traffic of people or vehicles.

### PRODUCT CHARACTERISTICS

<b>Color:</b>	Yellow, white, red and others on request
<b>Finish:</b>	Satin
<b>Weigh solid:</b>	65% ± 3
<b>Volume solid:</b>	55% ± 2
<b>VOC:</b>	450 g/L
<b>Density:</b>	1,35 g/cm <sup>3</sup> (valor aproximado)
<b>Flash point:</b>	23 °C
<b>Shelf life:</b>	24 months

### APPLICATIONS DATA

<b>Spreading rate per coat:</b>	<b>Minimum</b>	<b>Maximum</b>
	Wet – 150 µm	200 µm
	Dry – 80 µm	110 µm

#### Theoretical coverage:

6,67 m<sup>2</sup>/L to 80 µm  
5,00 m<sup>2</sup>/L to 110 µm

**Reducer:** TechSolv 9155 DEM. VIRÁRIA. - Dilute up to 15% by volume.  
Check environmental conditions first  
and application method

**Packaging:** 3,6 L, 20 L or 200 L

**Applications methods:** Airless Spray, Conventional Spray, Brush and Roller

### DRYING TIME

**Temperature** 25° C

**Clearance for traffic** 30 Minutes



# TECHNICAL DATA SHEET

**To recoat** 1 Hour - Unlimited

**To cure** 7 Days

## DRY HEAT RESISTANCE

Continuous 90°C/Discontinuous 120°C.

Organic coatings can change color, shine and adhesion when exposed to temperatures above 60°C.

## SURFACE PREPARATIONS

Every surface to be painted must be clean, dry and free from contaminants, such as: oils, salts, greases, fats, dust, etc. Wash with high pressure fresh water (HPFWW), as appropriate, and remove all oil or grease, soluble salts and any other contaminants, in accordance with the SSPC-SP1 solvent cleaning method.

Cement or concrete surfaces: these must be cured for at least 28 days. Whenever possible, it is recommended to prepare the surface before application with a solution of muriatic acid diluted in equal parts with water. Afterwards, wash with plenty of water until pH (7- 8). Allow to dry completely. Another alternative to open the porosity of the concrete is to sand with abrasive stone.

On aged paint: sand superficially and remove loose particles.

## APPLICATIONS METHOD

The product is supplied in a single packaging. Homogenize the package contents by means of mechanical or pneumatic agitation. Ensure that no sediment is trapped at the bottom of the package.

### Airless Spray:

**Use Airless**..... 60:1  
**Fluid pressure**.....1800 – 2000  
**Hose** ..... 3/8” inner diameter  
**Nozzle**.....0,015” to 0,019”

### Conventional Spray

**Gun**..... JGA 502/3 Devilbiss  
**Fluid Nozzle** ..... EX  
**Air cover**.....704  
**Atomization Pressure** ..... 60 - 65 psi  
**Pressure in the tank**.....10 to 20 psi

## SAFETY PRECAUTIONS

Before handling this product, it is essential to carefully read all the information contained in its chemical safety information sheet (MSDS), available on our website or request directly from our Customer Service (0800 487 777).

The surface preparation, handling and use of paints during painting and drying, as they are flammable products, must be carried out in ventilated places, away from flames, sparks or excessive heat, using personal protective equipment (PPE's) appropriate for the stage to be performed.

Contact with the skin can cause irritation.

Essas informações representam o melhor de nosso conhecimento à época de sua publicação. Lembramos que o bom resultado final da aplicação dos produtos depende de fatores que fogem ao nosso controle e que dizem respeito a preparação da superfície e conhecimentos técnicos do aplicador. A empresa reserva-se o direito de alterar essas especificações sem aviso prévio.



# TECHNICAL DATA SHEET

If swallowed, do not induce vomiting. In case of contact with eyes, wash them with plenty of water. In any case, seek medical attention immediately.

Do not smoke in the work area.

Make sure that the electrical installations are perfect and that they do not cause sparks.

Do not use thinner to clean the skin, hands and other parts of the body. To clean your hands use alcohol, then wash with water and appropriate cleaning pastes.

In case of fire, use CO<sub>2</sub> or chemical powder extinguishers. It is not recommended to use water to extinguish the fire produced by burning the paints.

Paints and thinners must be stored in ventilated areas and protected from weathering. The temperature can range from 10 to 40°C.

In the event of symptoms of intoxication by inhaling chemical vapors, the intoxicated person should be removed immediately from the workplace to ventilated areas.

In case of fainting, call a doctor immediately.

Product intended for use and handling by professionals connected to the painting area.

The application and use of this product must be carried out in compliance with all the National Health, Safety and Environment rules and regulations.

If it is necessary to carry out removals of the paint already applied and hardened from the substrate, the operator and people who are in the same environment must use personal protective equipment (PPE), appropriate as indicated in the safety information sheet (MSDS).

Store the product in sheltered, ventilated environments with a maximum temperature of 40°C. In situations that occur when welding metal parts painted with this product are required, dust and gases (smoke) will be released, which will require the use of equipment. appropriate personal protection (masks with activated carbon filters and even air conditioning equipment) according to each environment.

Applications in confined areas require adequate ventilation, in addition to specific methods and procedures. For these situations, contact your company's security department.

## NOTE

The practical performance of this product varies according to the thickness applied, method and technique of application, type and roughness of the substrate and environmental conditions, etc.

The values found for the tests of: specific weight and drying (with the specified thickness) were obtained in the laboratory at a temperature of 25°C. With temperatures different from that mentioned, the values established above tend to be different from those specified.

The instructions contained in this bulletin are based on our experience and technical knowledge, however, some factors are independent of our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

The use of a thinner other than that specified without the prior approval of the technical department of AnjoTech may affect the performance of the product and void its warranty.

We do not assume any liability for material and personal damage caused by the misuse of the information contained in this bulletin and the products mentioned.

This bulletin is subject to change without notice.

Essas informações representam o melhor de nosso conhecimento à época de sua publicação. Lembramos que o bom resultado final da aplicação dos produtos depende de fatores que fogem ao nosso controle e que dizem respeito a preparação da superfície e conhecimentos técnicos do aplicador. A empresa reserva-se o direito de alterar essas especificações sem aviso prévio.