

## TECHPOXI 0145

Conventional polyamide epoxy primer, two components. Quick drying product, excellent anticorrosive protection, free from heavy metals, with high hardness, excellent covering and filling power.

### RECOMMENDED USES

Indicated as an anticorrosive background in the preparation of metal surfaces in general, which will be exposed to humidity, chemical and physical attacks from low to medium aggressiveness. It can be applied in tanks, metal structures in general, machines, equipment, among others. Suitable for new works or maintenance and repairs.

### PRODUCT CHARACTERISTICS

<b>Color:</b>	White, gray and red oxide
<b>Finish:</b>	Matte
<b>Weigh solids:</b>	60 % $\pm$ 3
<b>Volume solids:</b>	45 % $\pm$ 2
<b>VOC:</b>	500 g/L
<b>Density:</b>	1,35 g/cm <sup>3</sup> (approximate value)
<b>Flash point:</b>	23 °C
<b>Shelf life:</b>	Part A: 24 months Part B: 06 months
<b>Pot-Life (25 °C):</b>	4 Hours

### APPLICATIONS DATA

<b>Spreading rate per coat:</b>	<b>Minimum</b>	<b>Maximum</b>
	Wet – 75 $\mu$ m	100 $\mu$ m
	Dry – 30 $\mu$ m	40 $\mu$ m
<b>Theoretical coverage:</b>	13,33 m <sup>2</sup> /L to 30 $\mu$ m 10,00 m <sup>2</sup> /L to 40 $\mu$ m	
<b>Reducer:</b>	TechSolv 9400 - Dilute up to 15% by volume.	
<b>Packaging:</b>	Part A: 2,88 L or 16 L Part B: 0,72 L or 04 L	
<b>Applications methods:</b>	Airless Spray, Conventional Spray, Brush and Roller	

<b>Mix Rate:</b>	<b>By mass</b>	<b>By Volume</b>
------------------	----------------	------------------



# TECHNICAL DATA SHEET

<b>Part A</b>	100,00	4
<b>Part B</b>	17,00	1

## DRYING TIME

<b>Temperature</b>	25° C
<b>To touch</b>	1 Hour
<b>To handle</b>	5 Hours
<b>To recoat</b>	8 - 48 Hours
<b>To cure</b>	7 Days

If maximum recoat time is exceeded, abrade surface before recoating. Drying time is a temperature, humidity, and film thickness dependent.

## APPLICATIONS CONDITIONS:

Relative humidity maximum to apply is 85%. Minimum temperature to apply and dry is 15 °C. Only apply if the surface is 3 °C above the dew point. Pot life is temperature dependent, therefore, keep the material avoiding direct sunlight.

## DRY HEAT RESISTANCE

Continuous heat: 90 °C. Organic coating may suffer changes in color, gloss and adhesion when exposed to temperatures above 60 °C.

## SURFACE PREPARATIONS

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile. Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

## APPLICATIONS METHOD

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

### Airless Spray:

<b>Pressure</b> .....	1800 - 2200 psi
<b>Hose</b> .....	1/4"
<b>Tip</b> .....	0,013" to 0,015"
<b>Filter</b> .....	Mesh 60

### Conventional Spray

Review date: 30/07/2020



# TECHNICAL DATA SHEET

**Gun**..... JGA 502/3 Devilbiss  
**Fluid Nozzle** ..... FX - FF  
**Atomization Pressure** ..... 50 psi  
**Fluid Pressure**..... 10 to 20 psi

## **Brush**

Brush.....Natural bristle.  
Reduction.....As needed up to 15% by volume.

## **Roller**

Cover:..... 3/8" woven with solvent resistant core.  
Reduction..... As needed up to 15% by volume.

## **APPLICATIONS PROCEDURES**

Mix contents of each component thoroughly with low speed power agitation. Make certain no pigment remains on the bottom of the can. Then combine 3 parts by volume of Part A with 1 part by volume of Part B. Thoroughly agitate the mixture with power agitation.

## **SAFETY PRECAUTIONS**

Refer to the SDS sheet before use.

## **NOTE**

The practical coverage is a dry thickness, applications method and surface profile dependent. Do not use a different thinner without the AnjoTech technical team approve. We do not assume any responsibility for material and personal damages caused by misuse of the information contained in this technical datasheet. Published technical data and instructions are subject to change without notice. Contact your AnjoTech representative for additional technical data and instructions.