

## REVOLUTION POLYESTER RESIN

### USE RECOMMENDATIONS

Polyester Resin with a high spreading rate, recommended for automotive refinishing applications in order to correct surface imperfections. Optimal adhesion to ferrous, galvanized, zined and aluminum substrates. Provides soft application, low porosity, high filling power and excellent sandability.

#### Chemical composition

Polyester resin, mineral fillers, additives, pigments and solvents.

### APPLICATION DATA

#### Catalysis and/or Dilution

100 parts per weight of Revolution Polyester Resin.  
2 to 3 parts per weight of catalyst for Polyester Filler

#### Application

Mix the resin well with the catalyst and apply with celluloid. Do not reinsert the already prepared mixture into the can. Avoid using excessive amounts of catalyst (over 3%) to prevent any painting defects, such as bleeding. To ensure perfect isolation, apply at least 2 crossed coats of PU Anjo Primer, waiting from 5 to 10 minutes between each coat.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

## **DRYING**

Final drying takes between 20 and 40 minutes. For optimal sandability, we recommend dry sanding with 120 or 150-grit sandpaper and finishing with 320-grit sandpaper.

## **SURFACE PREPARATION**

Sand the surface with 80-grit sandpaper to remove rust and traces of peeled paint. Anjo Paint Stripping Paste may also be used. Clean with Anjo Degreaser solution to eliminate dirt, oils, grease and residues in general. In case of parts with exposed chassis, the use of the Anjo Wash Primer is advised.

## **SAFETY RECOMMENDATION**

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- This is a flammable product. Keep away from sparks and sources of ignition. Do not smoke at the application site.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

## **COMMENTS**

The spreading rate of this product in practice will vary according to the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc. The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.